

CSP Program Summit 2016

High Performance Reduction/Oxidation Metal Oxides for Thermochemical Energy Storage (PROMOTES)

CSP: ELEMENTS DE-FOA-0000805

Duration: 3 years

Funding: DOE: \$3,450,000 Cost Share: \$909,793

Presenting: Andrea Ambrosini, Sandia National Laboratories


Project Team

- PI: James E. Miller (SNL)
- Sandia National Laboratories
 - Andrea Ambrosini, Sean M. Babiniec, Eric N. Coker, Ken Armijo, Clifford K. Ho
- Georgia Institute of Technology
 - Peter G. Loutzenhiser, Sheldon M. Jeter
- King Saud University
 - Hany Al Ansari
- Arizona State University
 - Ellen B. Stechel, Nathan G. Johnson

Problem Statement and Objective

Enabling technologies are needed to store and deliver thermal energy to high-temperature (> 1000 °C), high-efficiency power cycles, e.g. Air Brayton. The technology must be low cost ($$15/kWh_{th}$), which demands high energy density solutions.

We will systematically develop, characterize, and demonstrate a robust and innovative storage cycle based on novel metal oxides with *mixed ionic-electronic conductivity* (MIEC). Thermal energy is stored as chemical plus sensible potential in these materials through a reversible reduction-reoxidation reaction. The product of the cycle will be air at T $\geq 1000~^{\circ}$ C for integration with an air Brayton system. The tested system and validated models will indicate the ability to achieve thermal storage costs $\leq $15/kWh_{th}$ and total available enthalpy $\geq 1500~kJ/kg$.



Value Proposition


Thermochemical energy storage (TCES), wherein thermal energy is converted and stored indefinitely as chemical energy, can boost energy storage density. Redox active mixed ionic electronic conducting metal oxides (MIECs) with their elegantly simple redox chemistry, approach an ideal medium for high temperature TCES in many respects:

- They are robust and high temperature stable.
- The reduction/oxidation reactions are highly selective, highly reversible, and can be conducted open loop in air.
- MIEC properties enhance reaction kinetics.
- Particle approaches are complimentary to Falling Particle Receiver technology.
- Particulates can act as both a storage and heat transfer media.

We will capitalize on the unique characteristics of MIECs so that the potential of TCES may be realized.

Project Concept

- 1. New MIEC materials enable high temperature, high energy density storage
- 5. Systems and technoeconomics to predict cost and performance and to guide development efforts



- 2. SR3: A particle receiver tailored to metal oxide reduction reactions
- 3. Hot Storage Bin: High temperatures (T > 1000 °C) and an O₂free environment
- 4. ROx: Reoxidation reactor --replaces the combustor in a power block. Compressed air acts as both reactant and heat transfer fluid. High pO_2 facilitates heat recovery at high temperatures. Open cycle no gas storage.

Phase 1: Develop & Characterize materials & TE models


Phase 2: Midscale Component Development and Demo

Phase 3: Develop large-scale reactor and test on-sun

Milestones


SOPO Task # M.S. #	Task Title and Milestone Description (High Level)		
	, , , , , , , , , , , , , , , , , , ,		
1.1	Identify MIEC Material		
M1.1	Material identified that meets project metrics		
1.2	Design, Build and Validate Stagnation Flow Reactor		
M1.2	Validate that SFR can achieve necessary heating rates, be used to measure reaction kinetics, and be used to evaluate stability of materials		
1.3	Design of Storage Bins for 1000 °C, Reduced Particles		
M1.3	Storage materials identified consistent with project metrics		
1.4	Implement Thermodynamic and Techno-economics Models		
M1.4	Validate that the system can achieve sufficient thermal efficiency, exergy efficiency, and cost effectiveness		
2.1	Measure Reaction Kinetics		
M2.1	Demonstrate accurate determination of kinetic parameters		
2.2	Solar Receiver/Reactor/Reducer (SR3) Modeling and Design		
M2.2	Identify design that achieves receiver outlet > 1000 °C and meets project metrics		
2.3	Fabricate and Test Laboratory-scale SR3; Finalize Design of Demonstration-scale SR3		
M2.3	Demonstrate particle temperature between 1000 and 1350 °C at lab scale		
2.4	Evaluate Ability of ROx to Provide 1200°C at the Brayton State Points		
M2.4	Reactor design completed with modelling showing the ability to achieve sufficient power to the air Brayton powerblock under defined constraints		
2.5	Build and Test a Small Scale ROx Oxidizer Reactor		
M2.5	Ramp to 1200 °C in less than 5 minutes		
2.6	Balance of Plant Design		
M2.6	Cost-effective materials and components identified		
2.7	Benchmarked Thermodynamics System & Detailed Sub-system Models		
M2.7	Validate that the system can achieve sufficient thermal efficiency, exergy efficiency, and cost effectiveness		
3.1	Demonstration-Scale (≥100kWt) On-Sun System Testing		
M3.1	Successful demonstration		


1. Materials



Materials: Reaction Enthalpy

$$ABO_3 + \Delta H_{rxn} \leftrightarrow ABO_{3-\delta} + \delta/2 O_2(g)$$






- First generation: Investigated/characterized LSCM, LSCF, and related perovskite families to identify baseline composition, LSCM3891, with high redox capacity (δ = 0.46) and reasonable ΔH_{rxn} (242 kg/kJ)
- Second generation: Low-cost earth-abundant compositions CXM (X = Ti, Al)
 - Lower redox capacity compensated by higher $T_{red} \rightarrow$ Stronger M-O bonds and storage of higher-quality heat
 - Smaller molecular weight results in higher specific heat, and therefore mass-specific total enthalpy


Materials: Total Storage Capacity

$$\Delta H_{tot} = \Delta H_{rxn} + C_p \Delta T$$

Chemical + Sensible Energy Storage



Measured heat capacity as a function of temperature




Candidate material	Mol weight (g/mol)	T _{red} Onset (°C)	Max δ	ΔH_{rxn} (kJ/kg) (at δ_{max})	C _p (kJ/kg-K)	ΔH _{tot} (kJ/kg)
LSCM3791	209.5	343	0.461	242	*0.595	837
CTM28	141.6	901	0.293	393	*0.881	1274
CAM28	135.8	759	0.322	371	*0.910	1281

^{*}Estimated Values: C_p = 3R·N (J/mol-K) = 15R, T_{high} = 1200 °C, T_{low} = 200 °C


Materials: Cycle-to-Cycle Stability


Extended thermal redox cycling in TGA



Materials: Reaction Kinetics


"Upflow reactor" coupled to high flux solar simulator measures oxidation kinetics






Experimental data for CAM28 reduction (mass spectrometry, validated with GC) vs. models (lines)

Upward Flow Reactor (UFR) employs ultrafast heating rates > 50 K/s enabling measurement of MIEC kinetics.





2. Solar Receiver Reduction Reactor (SR3)



SR3: Inclined plane particle flow reactor modeling


Directly-irradiated inclined plane solar thermochemical reactor concept





Material properties for simplified mass and heat transfer model			
M-35 buster type alumina	k = 0.27 W/m·K ε = 0.5 for 0 < λ < 4 μ m ε = 0.95 for 4 < λ < 12 μ m ε = 0.8 for λ > 12 μ m		
Quartz Window	ε = 0.9 for 0 < λ < 0.1 μ m ε = 0.01 for 0.1 < λ < 5 μ m ε = 0.9 fr λ > 5 μ m		
Co ₃ O ₄ / CoO particles	k =7.5 - 10 W/m·K $\varepsilon_{\rm eff}$ = 0.85		


- Model couples heat and mass transfer (including particle flow) with chemical kinetics, reactor optics, and material limitations.
- Co₃ O₄ used as stand-in for CAM28 pending further data collection/refinement





CSP Program Summit 2016

SR3: Inclined plane particle flow reactor demonstration

Design and construction of lab-scale SR3 underway









(Left) Parametric study illustrating variation in average particle temperature and energy absorption efficiency as a function of particle bed thickness

Tilt rig constructed to characterize particulate flow down inclined planes and validate models in support of SR3 design and modeling



3. Hot Particle Storage



Hot Particle Storage

Design, cost, & thermal analysis of inert atmosphere hot particle storage bin

	Internal bin ter	nperature
	1000°C	1350°C
Temperature range in IFB (°C)	817-1000	1100-1350
Temperature range in PC (°C)	162-817	209-1100
Temperature range in EB (°C)	63-162	74-209
Temperature range in RC (°C)	45-63	51-74
Rate of heat loss (kW)	111	152
Heat loss to nitrogen (GJ)	2.0	2.7
Total energy loss over storage period (GJ)	5.2	4.4
Percentage loss of energy content	0.12%	0.18%



a.

Alumina-rich insulating firebrick

1.13e-03
1.10e-03
1.00e-03
1.00e-03
1.00e-03
2.0e-03
2.

Zirnorite 192


Chemical compatibility of insulating materials with MIECs: Zr-rich liners offer improved chemical resistance with thermal performance similar to conventional alumina firebrick.

	SRI HF- IB 1260	ZIRMUL	Zirnorite 699	Zirnorite 192	Silicon Carbide
Fe ₂ O ₃	R	R	NR	NR	NR
La _{0.8} Sr _{0.2} CoO ₃	R	R	NR	NR	NR
SrFe _{0.5} Co _{0.5} O _x	R	R	1	1	1
CaO	R	-	-	NR	NR
MgO	R	-	-	NR	1
$CaAl_{0.2}Mn_{0.8}O_3$	R	-	-	NR	NR
$CaTi_{0.2}Mn_{0.8}O_3$	R	-	-	NR	NR



Characterizing oxidation resistance of duct materials

4. ReOxidation Reactor (ROx)



4. ROx: Design, Modeling, Demonstration


Hot, reduced particles in

Counter-flow falling-particle design

- Flow pattern optimizes heat transfer and reaction kinetics
- Low pressure drop due to dispersed particles

Multi-phase, thermo-fluid modeling accomplished in ANSYS Fluent (right).


- Eulerian-Eulerian approach simulates particles as equivalent "fluid"
- Granular theory used for particle motion to capture particle-particle collisions
- Custom user-defined code to implement reactions



1A 1B 1C 1D 2A 2B 2C 2D

Fabricating a lab-scale (~2.5 kW) ROx demonstration unit – geometry optimized via Fluent modeling.


1-D model to bound parameter space, define inputs to 3D models



Functions of T: ρ_a , v_a , μ_a , Cp_a , Cp_p , Re/Nu/Pr, h, δ_{equil}

Oxidized particles out

5. Technoeconomics and Systems




5. Technoeconomic modeling


TE and performance models at various scales are continually updated and refined as new data is available. Information shown incorporates data for CAM28 and assumes a scale of 111.7 MWe.

Component List	Cost	% of Total
SR3	\$ 31,990,464	8.3%
Vacuum Pump	\$ 26,597,883	6.9%
Particles	\$ 11,123,973	2.9%
Tower	\$ 10,967,142	2.8%
Elevator	\$ 1,129,862	0.3%
Heat Exchange	\$ 1,865,733	0.5%
Storage Hot	\$ 3,593,935	0.9%
Storage Lower Hopper	\$ 2,355,678	0.6%
Storage Upper Hopper	\$ 1,247,124	0.3%
ROx Reactor	\$ 1,696,460	0.4%
Controls	\$ 3,523,857	0.9%
Solar Field	\$ 68,403,311	17.7%
Power Block	\$ 93,583,548	24.3%
Balance of Plant	\$ 16,276,905	4.2%
Contingency & Indirect	\$ 64,519,742	16.7%
Owner's Cost	\$ 46,640,498	12.1%
Multiple Components/Total	\$ 385,516,114	

- Particle inventory sensitive to temperature of the incoming air, SR3 operation, and the fabrication factor
 - Particle cost estimated at \$8.50/kWh_{th} based on CAM28 reduced at 1050 °C and 200 Pa pO₂ (δ =0.203), residual particle heat = 388 °C after ROx
- Storage volume scales with amount of particles, cost scales more slowly
 - Estimated at \$4.60/kW_{th}



Total system costs as a function of pO₂ and T assuming 2500 suns (2.5 MW/m²) at the aperture.



Storage cost as a function of energy density. Data points assume CAM 28 with the energy density varying as a function of the SR3 temperature and pO_2 .

Summary

- We have discovered and characterized a family of redox active MIEC oxides,
 CXM, which exhibit total enthalpies > 1200 kJ/kg
 - Stable at high temperatures
 - Reproducibly cycled with little loss in performance
 - Comprised of earth abundant elements
 - To our knowledge, these materials outperform any reported oxide TCES material operating above 1000 °C
- An inclined plane particle flow reactor was modeled and designed
 - A lab scale test rig was built to validate models
 - Construction of test reactor is underway.
- Designed storage bins and identified MIEC compatible liner materials
- A counter-flow falling-particle Re-oxidation (ROx) reactor was designed and will be constructed at lab scale
 - Multi-phase, thermo-fluid modeling accomplished in ANSYS Fluent
- Techno-economic modeling is underway, with constant refinement as new data is obtained
 - Current results show that the storage cost goal of \$15/kWh_{th} is achievable

Path to Market

The path to market strategy builds on previous experience and is composed of three elements:

- 1. Follow a system-level design strategy that leverages existing technology whenever possible
- 2. Provide a robust and scalable TCES solution
- 3. Partner with key players from the global CSP community to maximize deployment opportunity

Protecting the financial investments of potential commercial partners is considered critical, hence IP protection through the patent process is a priority. Filings to date include:

- US Application SD12749.1/S132468: Redox-active Oxide Materials for Thermal Energy Storage. (Ambrosini, Miller, Gill)
- Provisional patent application (62169109: Redox-active Oxide Materials for Thermal Energy Storage. (Babiniec, Coker, Miller, Ambrosini)
- Provisional patent application (62130847): An Air Brayton Cycle Integrated with Solar Thermochemical Storage. (Loutzenhiser, Jeter)

Thank You